

## Flowseal EPW (Coloured) Matt

### Product sheet

#### Product description

Flowseal EPW Matt is a 2-component water soluble epoxy sealer with high coverage.

#### Uses

Flowseal EPW Matt is used to paint and seal new and old concrete floors where there are requirements for dust-free, easy-to-clean floors with improved resistance to chemicals and wearing strength.

#### Environment & Health

Flowseal EPW Matt is solvent-free and practically odourless during application. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken. For more information, please refer to the safety datasheets for the individual components.

#### Ratio of components

1 part of component A is mixed with 2.3 parts of component B, by weight.

1 part of component A is mixed with 1.8 parts of component B, by volume.

20% water by weight of the unit (A+B) **must** be added to the mixed product for first coats and priming.

10% water by weight of the unit (A+B) **must** be added to the mixed product for subsequent coats.

**Note:** Once diluted, do **not** add further quantities of water.

Add all of Base A to Hardener B then add the water.

Mix with a slow speed drill and helical spinner, taking care not to entrain air.

#### Application temperature

The recommended substrate temperature is 15-25°C, but no less than 10°C.

The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening.

#### Application time/pot life

Ready-mixed product should be used within 40 minutes at a temperature of 18°C.

At higher temperatures the application time is shorter.

#### Curing time (at 20°C)

Can be overcoated after 12 hours

Can be walked on after 12 hours

Maximum overcoat time 24 hours

Low relative humidity, maximum 70 %, and good ventilation are prerequisites to achieve the above drying times. The product is fully hardened after 5-7 days.

Do not cover within first 24 hours of curing.

#### Colours

See System data sheet, Flowseal EPW.

**Solids content**

Flowseal EPW Matt approx. 60%

**Finish**

Matt.

**Density**

Component A approx. 1.11 kg/l.

Component B approx. 1.35 kg/l.

A+B approx. 1.28 kg/l.

**Storage**

12 months in unopened pack at a temperature of 5-40°C.  
Protect from weather and moisture / contaminant ingress.

**Packaging**

The product is delivered A+B in the following packs.

Unit	Base A	Hardener B
10.1 kg (8.0 litres)	3.1 kg	7.0 kg

*Any suggested practices or installation specifications for the composite floor or wall system (as opposed to individual product performance specifications) included in this communication (or any other) from Flowcrete UK Ltd constitute potential options only and do not constitute nor replace professional advice in such regard. Flowcrete UK Ltd recommends any customer seek independent advice from a qualified consultant prior to reaching any decision on design, installation or otherwise.*