

Flowfast Asphalt Primer (wht)

Product sheet

Product description

A 2-component low viscosity methyl methacrylate (MMA) based primer for filled asphalt and bitumen substrates. Flowfast Asphalt Primer will bond to surface dry substrates that have a Relative Humidity up to 95% (to BS 8204).

Note: Material is delivered in white coloured tins. Formerly named Flowfast Asphalt Primer (new).

Uses

For priming of asphalt/bitumen screeds, prior to overcoating with Flowfast resin toppings.

Environment & Health

Flowfast Asphalt Primer is a solvent free product but has an odour associated with it, ensure adequate ventilation and/or extraction. Follow the appropriate Occupational Health and Safety guidelines applicable to the location where the application is undertaken.

For more information, please refer to the safety datasheets for the individual components.

Ratio of components (by weight of Flowfast Asphalt Primer)

Temperature	Flowfast Catalyst	Pot life (approx.)	Curing time (approx.)
30°C	2%	8 minutes	25 minutes
20°C	3%	10 minutes	30 minutes
10°C	4%	12 minutes	45 minutes
0°C	5%	20 minutes	60 minutes

1g Flowfast Catalyst = 1.57 cm³ (1 cm³ Flowfast Catalyst = 0.64 g)

Add the required amount of catalyst to the resin. Mix with slow speed drill and helical spinner, taking care not to entrain air. Exceed the minimum application layer thickness to allow a continuous, unbroken resin film, which ensures full through cure. Re-apply a further layer if glossy or tacky patches are apparent after cure.

When applying thicker section or filled coatings, a light scatter of fine dry quartz must be applied into the wet primer to provide a mechanical key and to ensure that the coating is not applied too thinly; this prevents curing or adhesion problems in the coating.

When applying thin section coatings to the primer layer, no quartz scatter is required. However, the coatings must be applied to primer within 4-6 hours to prevent adhesion problems.

It is important to work with freshly mixed material; only mix enough that can be applied within the pot life guidelines given above.

Application temperature

The recommended substrate temperature is 10 - 25°C, but no less than 0°C and to a maximum of 30°C. The temperature of the substrate should exceed the "dew point" by 3°C during application and hardening. For application temperatures below 0°C, please consult Technical Department.

Colour

Transparent

Solids content

Approx. 100 %

Density

Approx. 1.0 kg/litre.

Storage

6 months in unopened pack.

Storage temperature between 5°C and 30°C (out of direct sunlight).

Flash point +10°C.

Protect from weather and moisture/contaminant ingress.

Packaging

The product is delivered in the following packs.

Unit

25 kg (25 litres)

180 kg (180 litres)

Any recommendation or suggestion relating to the use of the products made by Flowcrete UK Ltd., whether in its technical literature, or in response to a specific enquiry, or otherwise, is based upon data believed to be reliable, however the products and information are intended for use by Customers having requisite skill and know-how in the industry and therefore it is for the Customer to satisfy itself of the suitability of the products for its own particular use and it shall be deemed that the Customer has done so at its sole discretion and risk.